

## 沙特基础 Sabic>>

POE塑料是采用茂金属催化剂的乙烯和辛烯实现原位聚合的热塑性弹性体。

POE plastics are thermoplastic elastomers that use metallocene catalysts for the in-situ polymerization of ethylene and octene.

商标 Trademark	型号 Grade	密度 Density(g/cm <sup>3</sup> )	熔融指数 MI(g/10min)	邵氏硬度A Shore Hardness A	备注 Remarks
SABIC® FORTIFY™ POE	C5070D	0.868	11	63	C8
SABIC® FORTIFY™ POE	C1055D	0.857	2.2	55	C8
SABIC® FORTIFY™ POE	C1070D	0.868	2.0	71	C8
SABIC® FORTIFY™ POE	C1085	0.885	1.0	81	C8
SABIC® FORTIFY™ POE	C3080	0.880	3.0	78	C8